

REACH Status : Pre Registered

Product	Description				
CI Generic Name		Pigment Blue 15:3	SI Product Code	SO-PL 1004G	
CI No.		74160	CAS No.	147-14-8	
EINECS No.		205-685-1	Chemical Type	Cu,Phthalo Blue, Beta-Mod.	
Molecular Formula		C32H16CuN8	Molecular Weight	576	
Chemical Name: Copper,[29		9H , 31H-phthalocyanineato(Mass Tone : 0.2 %	ŀ	¹ Tint Tone : 1:10 Ratio
Physical Properties					
Sieve Residue (PPM) Max.					
Oil Absorption(gms)		45 - 60			
Bulk Density(gm/ml)		25 - 40			
Salt Content (%) Max.		1			
Moisture Content (%) Max.		1			
PH Value		5.5 – 8.5			
Fastness properties			Specification		
Heat °C	PP-Mass Tone	300°C / 5 min.	Coloristic properties (Tin	t)	Strength: ±5 %
Heat °C	PP-Tint Tone	300°C / 5 min.	Coloristic properties (Tin	t)	DA,DB,DE,DC,DH,DL: ±1
Light	Mass Tone	8	Light fastness : Scale 1	- 8	1~Poor & 8 ~ Excellent
Light	Tint Tone	8	Weather fastness : Scale	1- 5	1~Poor & 5~Excellent
Weather	Mass Tone	5	Migration : Scale	1- 5	1~Poor & 5 ~ Excellent
Weather	Tint Tone	-	Heat Stability °C		DE =3 at Maximum Tem<br with dwell time 5 minute

Application

Migration

PVC, Cable sheathing compounds, rubber, PO, PS, Engineering plastics, PP, PET, PA6 and PAN spin dyeing.

Note

The colors above have been generated electronically and should therefore not be used for comparison purposes. The colors are meant to give a first impression of the colorant shade.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our Product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

Regd. Office: 19307 Maifest Drive Cypress, Texas 77433-5234, United States Phone: +1 (832) -6400809 E-mail: info@solarimpex.com

5