

SOLAR IMPEX INC BELIEVING IN THE BEST

REACH Status: Pre Registered

Product Description				
CI Generic Name	Pigment Blue 15:3	SI Product Code	SO-CO 1004 G	
CI No.	74160	CAS No.	147-14-8	
EINECS No.	205-685-1	Chemical Type	Cu, Phthalo Blue, Beta-Modification	
Molecular Formula	C32H16CuN8	Molecular Weight	576	
Chemical Name: Conner [29H-nhthalocyanineato(2-)-N29 N30 N31 N32]- (SP-4-1)-				

Chemical Name: Copper,[29H-phthalocyanineato(2-)-N29,N30,N31,N32]-,(SP-4-1)

Physical Properties				
Sieve Residue (PPM) Max.	1000			
Oil Absorption(gms)	45 - 60			
Bulk Density(gm/ml)	25 - 40			
Salt Content (%) Max.	1			
Moisture Content (%) Max.	1			

Mass Tone: 5%	Tint Tone: 1:10 Ratio	

Fastness properties				
Heat °C		300		
Light	Mass Tone	8		
Light	Tint Tone	8		
Weather	Mass Tone	5		
Weather	Tint Tone	4-5		
Overspray		5		

Solvent Fastness properties		
Water	5	
Acid	5	
Alkali	5	
Ethanol	5	
MEK	4-5	
Mineral Spirit	5	

Application		Specification	
Automotive Paints	•	Coloristic Properties-Tint	Strength: <u>+</u> 5 %
Decorative Paints	•	Coloristic Properties-Tint	DA,DB,DE,DC,DH,DL: <u>+</u> 1
General Industrial Paints	•	Light fastness : Scale 1-8	1~Poor & 8 ~ Excellent
Powder Coatings	•	Weather fastness : Scale 1-5	1~Poor & 5 ~ Excellent
Coil Coating	•	Overspray : Scale 1-5	1~Poor & 5 ~ Excellent
•	recommended	Solvent Fastness: Scale 1-5	1~Poor & 5 ~ Excellent
0	limited suitability	SUIVEILL FASTILESS. SCALE 1-5 1 POOL & 5 EXCELEDIT	

Note:

The colors above have been generated electronically and should therefore not be used for comparison purposes. The colors are meant to give a first impression of the colorant shade. The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our Product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

Regd. Office: 19307 Maifest Drive Cypress, Texas 77433-5234, United States Phone: +1 (832) -6400809 E-mail: info@solarimpex.com