





**REACH Status: Pre Registered**

Product Description			
CI Generic Name	<b>Pigment Orange 5</b>	SI Product Code	<b>SO-CO 10330</b>
CI No.	12 075	CAS No.	3468-63-1
EINECS No.	222-429-4	Chemical Type	Beta-Naphthol
Molecular Formula	C16H10N4O5	Molecular Weight	338.27
Chemical Name: 1-[(2,4-dinitrophenyl)azo]-2-naphthol			

Physical Properties	
Sieve Residue (PPM) Max.	1000
Oil Absorption(gms)	50-65
Bulk Density(gm/ml)	15-35
Salt Content (%) Max.	1
Moisture Content (%) Max.	1

Mass Tone: 5%	Tint Tone: 1:10 Ratio
	

Fastness properties		
Heat °C		160
Light	Mass Tone	6
Light	Tint Tone	5-6
Weather	Mass Tone	3
Weather	Tint Tone	2
Overspray		-

Solvent Fastness properties	
Water	5
Acid	5
Alkali	5
Ethanol	3
MEK	2
Mineral Spirit	4

Application	
Automotive Paints	
Decorative Paints	•
General Industrial Paints	•
Powder Coatings	
Coil Coating	
•	recommended
o	limited suitability

Specification	
Coloristic properties-Tint	Strength : ± 5 %
Coloristic properties-Tint	DA,DB,DE,DC,DH,DL: ± 1
Light fastness : Scale 1- 8	1~Poor & 8 ~ Excellent
Weather fastness : Scale 1- 5	1~Poor & 5 ~ Excellent
Overspray : Scale 1- 5	1~Poor & 5 ~ Excellent
Solvent Fastness: Scale 1- 5	1~Poor & 5 ~ Excellent

**Note:**  
The colors above have been generated electronically and should therefore not be used for comparison purposes. The colors are meant to give a first impression of the colorant shade. The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our Product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

**Regd. Office:** 19307 Maifest Drive Cypress, Texas 77433-5234, United States  
**Phone:** +1 (832) -64000809 **E-mail:** [info@solarimpex.com](mailto:info@solarimpex.com)