

REACH Status :

Product Description					
CI Generic Name	Pigment Red 48:1	SI Product Code	SO-PL 1054		
CI No.	15 865:1	CAS No.	7585-41-3		
EINECS No.	231-494-8	Chemical Type	BONA,Ba		
Molecular Formula	C18H13CLN2O6S-Ba	Molecular Weight	556		
Chemical Name: 2-Naphthalenecarboxylic acid 4-[(5-chloro - 4- methyl -2-sulfonhenyl)azol 3- hydroxy - barium salt (1:1)					

Mass Tone : 0.2%

Physical Properties			
Sieve Residue (PPM) Max.	1000		
Oil Absorption(gms)	55 - 70		
Bulk Density(gm/ml)	20 - 40		
Salt Content (%) Max.	1		
Moisture Content (%) Max.	1		
PH Value	6.5 - 9		

Fastness properties				
Heat °C	PP-Mass Tone	230°C / 5 min.		
Heat °C	PP-Tint Tone	230°C / 5 min.		
Light	Mass Tone	6		
Light	Tint Tone	4		
Weather	Mass Tone	-		
Weather	Tint Tone	-		
Migration	I.	-		

Specification				
Coloristic properties (Tint)	Strength : ±5 %			
Coloristic properties (Tint)	DA,DB,DE,DC,DH,DL: ±1			
Light fastness : Scale- 1-8	1~Poor & 8 ~ Excellent			
Weather fastness : Scale 1- 5	1~Poor & 5 ~ Excellent			
Migration : Scale 1-5	1~Poor & 5 ~ Excellent			
Heat Stability °C	DE ≤3 at Maximum Temp. With dwell time 5 minutes.			

Tint Tone : 1:10 Ratio

Application

Plasticized & rigid PVC ,LDPE , Rubber

Note

The colors above have been generated electronically and should therefore not be used for comparison purposes. The colors are meant to give a first impression of the colorant shade.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our Product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

Regd. Office: 19307 Maifest Drive Cypress, Texas 77433-5234, United States Phone: +1 (832) -6400809 E-mail: info@solarimpex.com