

REACH Status: Pre Registered

Product Description				
CI Generic Name	Pigment Yellow 12	SI Product Code	SO-IN 1007	
CI No.	21 090	CAS No.	6358-85-6	
EINECS No.	228-787-8	Chemical Type	Diarylide Yellow	
Molecular Formula	C32H26CL2N6O4	Molecular Weight	630	
Chemical Name: Butanamide,2,2,-[3,3-dichloro{1,1-biphenyl}-4,4'-diyl)bis(azo)bis[3-oxo-N-phenyl				

Physical Properties		
Sieve Residue (PPM) Max.	1000	
Oil Absorption(gms)	60 - 75	
Bulk Density(gm/ml)	25 -40	
Salt Content (%) Max.	1	
Moisture Content (%) Max.	1	



Fastness properties			
Heat °C		180 °C	
Light	Mass Tone	5	
Light	Tint Tone	4	

Solvent Fastness properties	
Water	5
Acid	5
Alkali	5
Ethanol	5
MEK	4
Mineral Spirit	4-5

Application		
NC alcohol / NC acetate	Recommended	
Water based	Recommended	
Polyvinyl butyral / UV curing (Flexo)	highly recommended	
Metal deco	limited suitability	
Sheetfed	Recommended	
Heatset / Coldset/ UV curing (Offset)	highly recommended	

Specification			
Coloristic properties	Strength: ±5%		
Coloristic properties	DA,DB,DE,DC,DH,DL: ±1		
Light fastness : Scale 1-8	1~Poor & 8~Excellent		
Weather fastness : Scale 1-5	1~Poor & 5~Excellent		
Solvent Fastness: Scale 1-5	1~Poor & 5~Excellent		

The colors above have been generated electronically and should therefore not be used for comparison purposes. The colors are meant to give a first impression of the colors at shade

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our Product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

Regd. Office: 19307 Maifest Drive Cypress,Texas 77433-5234, United States Phone: +1 (832) -6400809 E-mail: info@solarimpex.com