

## **REACH Status : Pre Registered**

Product Description				
CI Generic Name	Pigment Yellow 13	SI Product Code	SO-IN 1008 O	
CI No.	21100	CAS No.	5102-83-0	
EINECS No.	225-822-9	Chemical Type	Diarylide Yellow	
Molecular Formula	C36H34CL2N6O4	Molecular Weight	686	
Chemical Name: Butanamide,2,2'-[(3,3'-dichloro{1,1'-biphenyl}-4,4'diyl)bis(azo)]bis[N-(2,4-dimethylphenyl)]-3-oxo				

Physical Properties		
Sieve Residue (PPM) Max.	1000	
Oil Absorption(gms)	60 - 75	
Bulk Density(gm/ml)	20 - 30	
Salt Content (%) Max.	1	
Moisture Content (%) Max.	1	

Mass Tone : 5%	Tint Tone : 1:9 Ratio

Fastness properties			Solven
Heat °C		200 °C	Water
Light	Mass Tone	4	Acid
Light	Tint Tone	4	Alkali
			Ethanol
			MEK
			Mineral

Solvent Fastness properties		
Water	5	
Acid	5	
Alkali	5	
Ethanol	5	
МЕК	4-5	
Mineral Spirit	5	

Application		Specification	
NC alcohol / NC acetate	Recommended	Coloristic properties	Strength : ± 5 %
Water based / UV curing (Flexo)	highly recommended	Coloristic properties	DA,DB,DE,DC,DH,DL: ±1
Polyvinyl butyral	Recommended	Light fastness : Scale 1-8	1~Poor & 8~Excellent
Metal deco	limited suitability		
Heatset / Coldset/	Recommended	Weather fastness : Scale 1-5	1~Poor & 5 ~ Excellent
Sheetfed / UV curing (Offset)	highly recommended	Solvent Fastness: Scale 1-5	1~Poor & 5 ~ Excellent

The colors above have been generated electronically and should therefore not be used for comparison purposes. The colors are meant to give a first impression of the colorant shade.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our Product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

Regd. Office: 19307 Maifest Drive Cypress,Texas 77433-5234, United States Phone: +1 (832) -6400809 E-mail: info@solarimpex.com