

REACH Status: Pre Registered

Salt Content (%)

Moisture Content (%) Max.

Product Description				
CI Generic Name	Pigment Yellow 3	SI Product Code	SO-IN 1006	
CI No.	11710	CAS No.	6486-23-3	
EINECS No.	229-355-1	Chemical Type	Monoazo Yellow	
Molecular Formula	C16H12Cl2N4O4	Molecular Weight	395.19688 g/mol	
Chemical Name: 2-[(4-chloro-2-nitrophenyl)azo]-N-(2-chlorophenyl)-3-oxobutyramide				

Physical Properties		
Sieve Residue (PPM) Max.	1000	
Oil Absorption(gms)	35 - 55	
Bulk Density(gm/ml)	20 - 40	

1

Mass Tone: 5%

Tint Tone: 1:9 Ratio

Fastness properties		
Heat °C		< 140 °C
Light	Mass Tone	6
Light	Tint Tone	6-7

Solvent Fastness properties		
Water	5	
Acid	5	
Alkali	5	
Ethanol	4	
MEK	3-4	
Mineral Spirit	4	

Application		
NC alcohol	Recommended	
Water based / Polyamide / UV curing (Flexo)	Highly recommended	
Polyvinyl butyral / NC acetate	limited suitability	
Sheetfed	Highly recommended	
UV curing (Offset)	Highly recommended	
Silkscreen	Recommended	

Specification		
Coloristic properties	Strength: ±5%	
Coloristic properties	DA,DB,DE,DC,DH,DL: ±1	
Light fastness : Scale 1-8	1~Poor & 8~Excellent	
Weather fastness : Scale 1-5	1~Poor & 5~Excellent	
Solvent Fastness: Scale 1-5	1~Poor & 5~Excellent	

The colors above have been generated electronically and should therefore not be used for comparison purposes. The colors are meant to give a first impression of the colorant shade.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our Product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

Regd. Office: 19307 Maifest Drive Cypress, Texas 77433-5234, United States Phone: +1 (832) -6400809 E-mail: info@solarimpex.com