

## **REACH Status : Pre Registered**

Product	Description

CI Generic Name	Pigment Yellow 74	SI Product Code	SO-CO 1014O
CI No.	11 741	CAS No.	6358-31-2
EINECS No.	228-768-4	Chemical Type	Monoazo Yellow
Molecular Formula	C18H18N4O6	Molecular Weight	386.36
Chemical Name: 2-[(2-methoxy-4-nitrophenyl)azo]-N-(2-methoxyphenyl)-3-oxobutyramide			

Physical Properties		
Sieve Residue (PPM) Max.	1000	
Oil Absorption(gms)	45-60	
Bulk Density(gm/ml)	25-40	
Salt Content (%) Max.	1	
Moisture Content (%) Max.	1	

Mass Tone : 5%	Tint Tone : 1:10 Ratio

Fastness properties		
Heat °C		140
Light	Mass Tone	7-8
Light	Tint Tone	7-8
Weather	Mass Tone	4-5
Weather	Tint Tone	3-4
Overspray		4-5

So	lvent	Fastnes	s propert	ies

Water	5
Acid	5
Alkali	5
Butanol	3-4
MEK	3
White Spirit	4

Application		Specification		
Automotive Paints		Coloristic properties -Tint Strength : ± 5 %		
Decorative Paints	•	Coloristic properties - Tint DA,DB,DE,DC,DH,DL: ±1		
General Industrial Paints	0	Light fastness : Scale 1-8 1~Poor & 8 ~ Excellent		
Powder Coatings		Weather fastness : Scale 1-5 1~Poor & 5 ~ Excellent		
Coil Coating		Overspray :         Scale 1-5         1~Poor & 5 ~ Excellent		
•	recommended	Colored Forder and Color 4, Ford AnDrew 9, Ford Fordland		
0	limited suitability	Solvent Fastness: Scale 1-5 1~Poor & 5 ~ Excellent		

## Note:

The colors above have been generated electronically and should therefore not be used for comparison purposes. The colors are meant to give a first impression of the colorant shade.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our Product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

 Regd. Office: 19307 Maifest Drive Cypress, Texas 77433-5234, United States

 Phone: +1 (832) -6400809
 E-mail: info@solarimpex.Com